



## FORMING GUIDELINES

1. Remove blue or clear film from both sides of plastic before heating.  
\*Tru-Tain DX material may be formed with film on if you wish
2. Turn on the heating element of the vacuum machine. Allow 2-3 mins to pre-heat; heating element will be orange
3. Place plastic into vacuum frame & close. Slide frame with plastic up toward heading element, swing heater over to heat plastic
4. Heat Tru-Tain DX plastic & splints until ½ inch sag appears, turn vacuum on and slide frame with plastic over model
5. Leave vacuum on for 20-25 seconds, let cool or spray with Insta-Cool® for immediate handling
6. Remove and trim

SURGICAL SPLINT						
Thickness	.020 (0.5MM)	.030 (0.75MM)	.040 (1.0MM)	.060 (1.5MM)	.080 (2.0MM)	.100 (2.5MM)
BioSTAR	Code 103	Code 103	Code 113	Code 133	Code 184	Code 204
MiniSTAR	Code 113	Code 113	Code 123	Code 143	Code 194	Code 214
MiniSTAR S	Code 113	Code 123	Code 133	Code 153	Code 204	Code 224
Druformat	Heating - 0:55	Heating - 1:00	Heating - 1:05	Heating - 1:30	Heating - 1:50	Heating - 2:05
	Cooling - 1:15	Cooling - 1:25	Cooling - 1:35	Cooling - 1:50	Cooling - 2:00	Cooling - 2:20

\*MiniSTAR/ BioSTAR are trademarks of Scheu Dental Technology. Druformat Scan is trademark of Dreve Dentomid.